

GARR TOOL High Performance Milling Guide for 846MA, 853MA, 855MA, 863MA

	ISO Material	HRC	M/Min. (Vc)	CHIPLOAD PER TOOTH (Fz)									
				3.0mm	5.0mm	6.0mm	8.0mm	10.0mm	12.0mm	16.0mm	20.0mm	25.0mm	
S	COBALT BASE ALLOYS												
	Powdered Metal, Stellite, Hs-21, Haynes 25/188, X-40, L-605	<40 >40	28 - 43 20 - 35	.020 - .051 .013 - .038	.010 - .025 .010 - .018	.018 - .030 .013 - .028	.025 - .046 .020 - .036	.025 - .051 .025 - .043	.046 - .071 .038 - .064	.058 - .079 .053 - .071	.069 - .086 .061 - .076	.074 - .091 .064 - .079	
	NICKEL BASE ALLOYS												
	Invar, Kovar, Inconel-625/718, Waspaloy, Rene, Hastelloy, A286	<40 >40	26 - 43 22 - 35	.013 - .023 .008 - .020	.013 - .023 .010 - .018	.018 - .033 .018 - .030	.025 - .041 .023 - .038	.025 - .051 .025 - .046	.051 - .071 .038 - .064	.064 - .081 .056 - .076	.074 - .091 .066 - .084	.076 - .097 .074 - .089	
	IRON BASE ALLOYS												
	Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpenter 22-b3	<40 >40	26 - 43 22 - 35	.013 - .025 .008 - .020	.020 - .025 .010 - .020	.015 - .030 .013 - .025	.018 - .038 .015 - .033	.028 - .041 .020 - .036	.046 - .066 .033 - .058	.064 - .076 .056 - .071	.066 - .086 .064 - .079	.081 - .097 .076 - .089	
	MONEL												
Monel - 65% Nickel		22 - 43	.010 - .025	.020 - .030	.023 - .038	.025 - .041	.025 - .051	.056 - .079	.066 - .084	.074 - .091	.076 - .097		
TITANIUM ALLOYS													
Commercially Pure, 6Al-4V, Astrm 1/2/3, 6Al-25N-4Zr-2Mo-Si		49 - 69	.013 - .025	.013 - .030	.020 - .038	.025 - .056	.046 - .069	.058 - .081	.064 - .084	.069 - .089	.071 - .094		
5553 / Beta Titanium		39 - 59	.010 - .025	.010 - .025	.015 - .036	.020 - .041	.038 - .064	.056 - .071	.061 - .076	.066 - .081	.071 - .089		
M	STAINLESS STEELS												
	13/8, 15/5, 17-4, PH Types	<40 >40	53 - 69 69 - 89	.013 - .018 .005 - .010	.010 - .020 .005 - .015	.018 - .025 .007 - .018	.020 - .030 .010 - .020	.033 - .046 .018 - .030	.025 - .051 .020 - .038	.030 - .064 .025 - .041	.030 - .051 .033 - .043	.051 - .071 .038 - .051	
	200 Series, 300 Series	<40 >40	31 - 49 69 - 108	.008 - .018 .005 - .013	.013 - .023 .010 - .018	.020 - .038 .013 - .025	.025 - .046 .020 - .030	.025 - .046 .023 - .038	.038 - .064 .033 - .046	.046 - .071 .038 - .058	.056 - .081 .043 - .064	.064 - .102 .056 - .102	
	304L, 316L, Nitronic 50	<40 >40	79 - 89 61 - 79	.008 - .018 .005 - .013	.013 - .025 .010 - .018	.020 - .038 .013 - .025	.023 - .033 .013 - .025	.025 - .046 .018 - .025	.038 - .051 .023 - .038	.046 - .056 .030 - .046	.046 - .089 .038 - .064	.058 - .091 .051 - .076	
	400 Series	<40 >40	79 - 89 59 - 79	.018 - .025 .010 - .020	.023 - .038 .015 - .025	.023 - .036 .018 - .028	.028 - .038 .020 - .030	.033 - .046 .023 - .038	.038 - .064 .030 - .051	.051 - .089 .046 - .076	.056 - .102 .051 - .089	.076 - .117 .061 - .107	
	HIGH STRENGTH TOOL STEELS												
A2, D2, P20, H13, S2, O1	<40 >40	89 - 128 59 - 89	.013 - .020 .008 - .013	.020 - .038 .013 - .025	.038 - .051 .020 - .030	.038 - .058 .025 - .038	.038 - .064 .025 - .046	.051 - .076 .038 - .051	.051 - .076 .038 - .051	.064 - .089 .046 - .064	.076 - .102 .051 - .076		
MEDIUM ALLOY TOOL STEELS													
4140, 4340, 52100, 6150, 8620	<40 >40	89 - 128 59 - 89	.013 - .020 .008 - .013	.020 - .038 .013 - .025	.038 - .051 .020 - .030	.038 - .058 .025 - .038	.038 - .064 .025 - .046	.051 - .076 .038 - .051	.051 - .076 .038 - .051	.064 - .089 .046 - .064	.076 - .102 .051 - .076		
CARBON STEELS													
1000's - 1018, 1020, 12L14	<40 >40	89 - 128 59 - 89	.013 - .020 .008 - .013	.020 - .038 .013 - .025	.038 - .051 .020 - .030	.038 - .058 .025 - .038	.038 - .064 .025 - .046	.051 - .076 .038 - .051	.051 - .076 .038 - .051	.064 - .089 .046 - .064	.076 - .102 .051 - .076		
CAST STEELS													
Steel		69 - 108	.015 - .025	.023 - .046	.030 - .051	.038 - .058	.046 - .064	.051 - .076	.071 - .091	.076 - .102	.089 - .114		
K	CAST MATERIAL												
	Ductile Iron		89 - 128	.025 - .038	.038 - .051	.051 - .076	.064 - .089	.064 - .089	.076 - .114	.102 - .127	.102 - .127	.127 - .152	
Gray Iron		118 - 157	.038 - .064	.051 - .076	.064 - .089	.076 - .102	.076 - .102	.102 - .127	.127 - .152	.152 - .178	.152 - .178		
N	NON-FERROUS												
	Aluminum		118 - 197	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178	.173 - .229	
	Magnesium		118 - 197	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178	.173 - .229	
	Copper		98 - 177	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178	.173 - .229	
Brass, Bronze		79 - 157	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178	.173 - .229		
O	COMPOSITE (non-ISO)												
	Fiberglass, Plastics		79 - 157	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178	.173 - .229	
	Graphite, G10	(See Graphite Chart - page 311)											

Beryllium added to any material adds hardness and some nickel content. If tool displays chatter, increase feed (IPM) up to 30% and reduce speed (RPM) by 10%.
More detailed information is available on succeeding pages regarding the following materials: Aluminum, High Rockwell Steels, Graphite, and VRX end mills

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.