

GARR TOOL Drilling Guide

Fractional

Type	Rc Hardness	CHIPLOAD PER FLUTE (Fz)				
		1/16" - 1/8"	1/8" - 1/4"	1/4" - 3/8"	3/8" - 1/2"	1/2" - 5/8"
COBALT BASE ALLOYS						
Powdered Metal, Stellite, Hs-21, Haynes 25/188, X-40, L-605	< 35	.0004" - .0010"	.0008" - .0020"	.0015" - .0025"	.0020" - .0040"	.0025" - .0050"
	> 35	.0004" - .0010"	.0005" - .0010"	.0010" - .0015"	.0010" - .0020"	.0015" - .0030"
NICKEL BASE ALLOYS						
Invar, Kovar, Inconel-625/718, Waspalloy, Rene, Hastalloy, A286	< 35	.0005" - .0015"	.0010" - .0015"	.0015" - .0025"	.0020" - .0040"	.0025" - .0050"
	> 35	.0004" - .0010"	.0008" - .0015"	.0010" - .0015"	.0015" - .0030"	.0020" - .0040"
IRON BASE ALLOYS						
Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpenter 22-b3	< 35	.0010" - .0015"	.0010" - .0020"	.0015" - .0035"	.0020" - .0050"	.0030" - .0060"
	> 35	.0008" - .0015"	.0010" - .0020"	.0015" - .0025"	.0020" - .0040"	.0025" - .0050"
MONEL						
Monel - 65% Nickel		.0004" - .0010"	.0008" - .0015"	.0010" - .0015"	.0015" - .0030"	.0020" - .0040"
TITANIUM ALLOYS						
Commercially Pure, 6Al-4V, Astm 1/2/3, 6Al-25N-4Zr-2Mo-Si		.0008" - .0015"	.0010" - .0020"	.0015" - .0030"	.0020" - .0040"	.0025" - .0050"
STAINLESS STEELS						
(Precipitation) 13/8, 15/5, 17-4, pH Types	< 35	.0005" - .0015"	.0010" - .0020"	.0015" - .0035"	.0020" - .0040"	.0025" - .0050"
	> 35	.0004" - .0010"	.0008" - .0015"	.0010" - .0015"	.0015" - .0030"	.0020" - .0040"
(Austenitic) Inox, 200 Series, 300 Series	< 35	.0005" - .0015"	.0010" - .0020"	.0015" - .0035"	.0020" - .0040"	.0025" - .0050"
	> 35	.0004" - .0010"	.0008" - .0015"	.0010" - .0015"	.0015" - .0030"	.0020" - .0040"
(Austenitic) 304L, 316L, Nitronic 50, Inox	< 35	.0004" - .0010"	.0008" - .0015"	.0010" - .0015"	.0015" - .0030"	.0020" - .0040"
	> 35	.0003" - .0008"	.0005" - .0010"	.0010" - .0015"	.0010" - .0020"	.0015" - .0030"
(Martensitic) 400 Series	< 35	.0005" - .0015"	.0010" - .0020"	.0015" - .0035"	.0020" - .0040"	.0025" - .0050"
	> 35	.0004" - .0010"	.0008" - .0015"	.0010" - .0015"	.0015" - .0030"	.0020" - .0040"
HIGH STRENGTH TOOL STEELS						
4140, 4340, 6150, 5210, A2, D2, P20, H11, H13, S2, O1	< 35	.0005" - .0015"	.0010" - .0020"	.0015" - .0025"	.0015" - .0030"	.0020" - .0040"
	> 35	.0004" - .0010"	.0010" - .0020"	.0010" - .0020"	.0015" - .0030"	.0020" - .0040"
MEDIUM ALLOY TOOL STEELS						
200, 250, 300, 8620	< 35	.0010" - .0015"	.0015" - .0025"	.0020" - .0030"	.0020" - .0040"	.0025" - .0050"
	> 35	.0005" - .0010"	.0010" - .0015"	.0010" - .0025"	.0015" - .0030"	.0020" - .0040"
CARBON STEELS						
Platinum, A36, 12L14, 1000's, 1100's, 1300's	< 35	.0010" - .0015"	.0015" - .0025"	.0020" - .0030"	.0020" - .0040"	.0025" - .0050"
	> 35	.0005" - .0010"	.0010" - .0020"	.0010" - .0025"	.0015" - .0035"	.0020" - .0040"
CAST MATERIAL						
Steel		.0008" - .0015"	.0010" - .0020"	.0015" - .0030"	.0020" - .0040"	.0025" - .0050"
Ductile Iron		.0010" - .0020"	.0010" - .0030"	.0015" - .0035"	.0025" - .0040"	.0030" - .0050"
Gray Iron		.0010" - .0020"	.0010" - .0030"	.0015" - .0035"	.0025" - .0040"	.0030" - .0050"
Aluminum		.0010" - .0020"	.0015" - .0040"	.0020" - .0050"	.0030" - .0060"	.0035" - .0070"
ALUMINUM						
Aircraft Grade (6061, 7075)		.0010" - .0020"	.0015" - .0040"	.0020" - .0050"	.0030" - .0060"	.0035" - .0070"
MAGNESIUM						
		.0010" - .0020"	.0010" - .0030"	.0015" - .0035"	.0025" - .0040"	.0030" - .0050"
COPPER						
Copper Alloys		.0010" - .0020"	.0010" - .0030"	.0015" - .0035"	.0025" - .0040"	.0030" - .0050"
BRASS, BRONZE						
Brass, Aluminum/Bronze, Low Silicon Bronze		.0010" - .0020"	.0010" - .0030"	.0015" - .0035"	.0025" - .0040"	.0030" - .0050"
		.0008" - .0015"	.0010" - .0020"	.0015" - .0030"	.0020" - .0040"	.0025" - .0050"
COMPOSITE MATERIAL						
Glass Epoxy, Fiberglass, Plastics, Graphite, G10		.0010" - .0020"	.0010" - .0030"	.0015" - .0035"	.0025" - .0040"	.0030" - .0050"

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.