

GARR TOOL Milling Guide for High Rc Finishers in Hardened Steel


Fractional

(Reference series: 545MA, 545BA, 545RA, VRX)

DIAMETER	38 - 45 HRc		45 - 50 HRc		50 - 55 HRc		55 - 60 HRc		60 - 65 HRc		65 - 70 HRc	
	RPM	CPT (Fz)	RPM	CPT (Fz)	RPM	CPT (Fz)	RPM	CPT (Fz)	RPM	CPT (Fz)	RPM	CPT (Fz)
1/8"	13750	.0009"	7650	.0008"	5350	.0006"	3820	.0005"	2300	.0004"	1850	.0003"
3/16"	9200	.0012"	5100	.0010"	3570	.0008"	2550	.0007"	1530	.0006"	1225	.0004"
1/4"	6900	.0015"	3850	.0012"	2675	.0010"	1910	.0008"	1150	.0007"	925	.0006"
3/8"	4600	.0018"	2550	.0015"	1800	.0012"	1275	.0010"	765	.0009"	615	.0008"
1/2"	3450	.0022"	1950	.0018"	1350	.0014"	955	.0012"	575	.0012"	460	.0010"
5/8"	2750	.0027"	1550	.0022"	1100	.0020"	765	.0018"	460	.0015"	370	.0013"
3/4"	2300	.0030"	1275	.0027"	900	.0025"	640	.0022"	390	.0017"	310	.0017"
1"	1720	.0033"	960	.0030"	675	.0027"	480	.0025"	290	.0023"	230	.0019"

Profiling / Side Cutting	
Axial (ap)	1xD
Radial (ae)	5% of Dia.

Slotting / Pocket Milling	
Axial (ap)	5% of Dia.
Radial (ae)	1xD



High Speed Machining

DIAMETER	38 - 45 HRc		45 - 50 HRc		50 - 55 HRc		55 - 60 HRc		60 - 65 HRc		65 - 70 HRc	
	RPM	CPT (Fz)	RPM	CPT (Fz)	RPM	CPT (Fz)	RPM	CPT (Fz)	RPM	CPT (Fz)	RPM	CPT (Fz)
1/8"	36670	.0006"	30600	.0005"	24500	.0004"	18340	.0004"	13750	.0003"	11460	.0002"
3/16"	24450	.0009"	20400	.0008"	16300	.0006"	12230	.0005"	9200	.0004"	7650	.0003"
1/4"	18340	.0012"	15300	.0010"	12230	.0008"	9200	.0007"	6900	.0005"	5750	.0004"
3/8"	12225	.0015"	10200	.0012"	8150	.0010"	6100	.0008"	4600	.0007"	3850	.0006"
1/2"	9170	.0018"	7650	.0015"	6100	.0012"	4600	.0010"	3450	.0009"	2870	.0008"
5/8"	7335	.0022"	6100	.0018"	4900	.0014"	3700	.0012"	2750	.0011"	2300	.0010"
3/4"	6115	.0027"	5100	.0022"	4100	.0020"	3100	.0018"	2300	.0014"	1900	.0013"
1"	4585	.0030"	3820	.0027"	3100	.0025"	2300	.0022"	1720	.0019"	1450	.0017"

Profiling / Side Cutting	
Axial (ap)	1xD
Radial (ae)	2% of Dia.

Slotting / Pocket Milling	
Axial (ap)	2% of Dia.
Radial (ae)	1xD

D = Tool Diameter

Example: 2% of Dia., when D = 1/2" (.02 x .500") = .010" per pass

Preferable method is to run tools with air blast to keep chips away from the cutting edge.
If air is not available, either coolant spray or dry machining is acceptable.

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.