

GARR TOOL Milling Guide for Drill Mills

* Chamfering *

TECHNICAL

	ISO Material	HRC	M/Min. (Vc) 154M, 154MA 152M, 152MA	CHIPLOAD PER TOOTH (Fz)										
				3.0mm	4.0mm	5.0mm	6.0mm	8.0mm	10.0mm	12.0mm	16.00mm	20.0mm		
S	COBALT BASE ALLOYS													
	Powdered Metal, Stellite, Hs-21, Haynes 25/188, X-40, L-605	< 40 > 40	24 - 35 20 - 31	.010 - .020 .008 - .015	.010 - .020 .008 - .015	.010 - .020 .008 - .015	.013 - .025 .008 - .020	.020 - .038 .013 - .025	.025 - .046 .020 - .038	.038 - .076 .025 - .038	.051 - .076 .038 - .064	.064 - .089 .038 - .051		
	NICKEL BASE ALLOYS													
	Invar, Kovar, Inconel-625/718, Waspaloy, Rene, Hastelloy, A286	< 40 > 40	22 - 35 18 - 31	.010 - .020 .008 - .015	.010 - .020 .008 - .015	.010 - .020 .008 - .015	.013 - .025 .008 - .020	.020 - .038 .013 - .025	.025 - .046 .020 - .038	.038 - .076 .025 - .038	.051 - .076 .038 - .064	.064 - .089 .038 - .051		
	IRON BASE ALLOYS													
	Incoloy 800-802, Multimet N-155, Timkin 16-25-6, Carpenter 22-b3	< 40 > 40	22 - 35 20 - 31	.010 - .020 .008 - .015	.010 - .020 .008 - .015	.010 - .020 .008 - .015	.013 - .025 .008 - .020	.020 - .038 .013 - .025	.025 - .046 .020 - .038	.038 - .076 .025 - .038	.051 - .076 .038 - .064	.064 - .089 .038 - .051		
	MONEL													
Monel - 65% Nickel		20 - 31	.008 - .020	.008 - .020	.013 - .030	.013 - .030	.020 - .038	.025 - .038	.033 - .051	.046 - .064	.051 - .076			
TITANIUM ALLOYS														
Commercially Pure, 6Al-4V, Astm 1/2/3, 6Al-25N-4Zr-2Mo-Si		20 - 31	.008 - .020	.008 - .020	.013 - .030	.013 - .030	.020 - .038	.025 - .038	.033 - .051	.046 - .064	.051 - .076			
5553 / Beta Titanium		35 - 47	.008 - .020	.008 - .020	.010 - .025	.010 - .025	.013 - .030	.020 - .036	.025 - .041	.025 - .051	.038 - .064			
M	STAINLESS STEELS													
	(Precipitation) 13/8, 15/5, 17-4, pH Types	< 40 > 40	39 - 59 31 - 39	.008 - .015 .005 - .010	.008 - .015 .005 - .010	.008 - .018 .005 - .015	.015 - .023 .008 - .018	.020 - .030 .010 - .020	.033 - .046 .018 - .030	.025 - .051 .020 - .038	.030 - .064 .025 - .041	.030 - .051 .033 - .043		
	(Austenitic) 200 Series, 300 Series	< 40 > 40	59 - 89 49 - 87	.005 - .015 .008 - .013	.005 - .015 .008 - .013	.013 - .020 .008 - .018	.020 - .038 .013 - .025	.038 - .046 .020 - .030	.025 - .046 .018 - .030	.038 - .064 .033 - .046	.046 - .071 .038 - .058	.056 - .081 .043 - .064		
	(Austenitic) 304L, 316L, Nitronic 50	< 40 > 40	39 - 59 31 - 39	.008 - .018 .005 - .013	.008 - .018 .005 - .013	.013 - .025 .010 - .018	.020 - .038 .013 - .025	.023 - .033 .013 - .025	.025 - .046 .018 - .025	.038 - .051 .023 - .038	.046 - .056 .030 - .046	.046 - .089 .038 - .064		
	(Martensitic) 400 Series	< 40 > 40	59 - 79 39 - 59	.018 - .025 .010 - .020	.018 - .025 .010 - .020	.023 - .038 .015 - .025	.023 - .036 .018 - .028	.028 - .038 .020 - .030	.033 - .046 .023 - .038	.038 - .064 .030 - .051	.051 - .089 .046 - .076	.056 - .102 .051 - .089		
	HIGH STRENGTH TOOL STEELS													
	4140, 4340, 6150, 5210, A2, D2, P20, H11, H13, S2, O1	< 40 > 40	59 - 79 39 - 59	.008 - .020 .008 - .013	.008 - .020 .008 - .013	.013 - .025 .008 - .020	.025 - .038 .013 - .025	.030 - .051 .013 - .025	.030 - .051 .013 - .025	.036 - .061 .025 - .038	.046 - .066 .030 - .046	.051 - .071 .036 - .051		
MEDIUM ALLOY TOOL STEELS														
200, 250, 300, 8620	< 40 > 40	59 - 79 39 - 59	.008 - .020 .008 - .013	.008 - .020 .008 - .013	.013 - .025 .008 - .020	.025 - .038 .013 - .025	.030 - .051 .013 - .025	.030 - .051 .013 - .025	.036 - .061 .025 - .038	.046 - .066 .030 - .046	.051 - .071 .036 - .051			
LOW CARBON STEELS														
Platinum, A36, 12L14, 1000's, 1100's, 1300's	< 40 > 40	59 - 79 39 - 59	.008 - .020 .008 - .013	.008 - .020 .008 - .013	.013 - .025 .008 - .020	.025 - .038 .013 - .025	.030 - .051 .013 - .025	.030 - .051 .013 - .025	.036 - .061 .025 - .038	.046 - .066 .030 - .046	.051 - .071 .036 - .051			
CAST STEELS														
Steel		49 - 69	.008 - .020	.008 - .020	.013 - .025	.025 - .046	.025 - .046	.031 - .051	.038 - .064	.061 - .081	.066 - .086			
K	CAST MATERIAL													
	Ductile Iron		69 - 89	.020 - .031	.023 - .035	.025 - .038	.038 - .064	.038 - .064	.051 - .076	.064 - .089	.089 - .114	.089 - .114		
Gray Iron		69 - 89	.020 - .031	.023 - .035	.025 - .038	.038 - .064	.038 - .064	.051 - .076	.064 - .089	.089 - .114	.089 - .114			
N	NON-FERROUS													
	Aluminum (6061, 7075)		118 - 197	.015 - .025	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178		
	Magnesium		118 - 197	.015 - .025	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178		
	Copper		98 - 177	.015 - .025	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178		
Brass, Bronze		98 - 157	.015 - .025	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178			
O	COMPOSITE (non-ISO)													
	Glass Epoxy, Fiberglass, Plastics		79 - 157	.015 - .025	.015 - .025	.020 - .036	.030 - .051	.036 - .071	.051 - .076	.089 - .122	.127 - .152	.147 - .178		

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.