

GARR TOOL Milling Guide for Die Mold Cutters


Roughing

(Reference series: 350MX)

DIAMETER	RPM		CHIPLOAD PER TOOTH (Fz)	
	40 - 50 HRC	50 - 60 HRC	40 - 50 HRC	50 - 60 HRC
1/32"	20,000 - 40,000	20,000 - 40,000	.0005" - .0007"	.0004" - .0005"
1/16"	20,000 - 40,000	20,000 - 40,000	.0010" - .0015"	.0008" - .0010"
3/32"	20,000 - 32,000	20,000 - 30,000	.0015" - .0020"	.0010" - .0015"
1/8"	18,000 - 24,000	15,000 - 20,000	.0020" - .0025"	.0015" - .0020"
3/16"	12,000 - 16,000	10,000 - 14,000	.0030" - .0040"	.0020" - .0030"
1/4"	9,000 - 12,000	7,500 - 10,000	.0040" - .0050"	.0025" - .0040"
5/16"	7,000 - 10,000	6,000 - 8,500	.0050" - .0065"	.0035" - .0050"
3/8"	6,000 - 8,000	5,000 - 7,000	.0060" - .0075"	.0045" - .0060"
1/2"	4,500 - 6,000	4,000 - 5,500	.0080" - .0100"	.0055" - .0080"
5/8"	3,500 - 5,000	3,000 - 4,500	.0090" - .0110"	.0065" - .0090"
3/4"	3,000 - 4,000	2,500 - 3,500	.0100" - .0120"	.0075" - .0100"
1"	2,300 - 3,000	2,000 - 2,500	.0110" - .0130"	.0085" - .0110"

Semi-Finishing and Finishing

DIAMETER	RPM		CHIPLOAD PER TOOTH (Fz)	
	40 - 50 HRC	50 - 60 HRC	40 - 50 HRC	50 - 60 HRC
1/32"	20,000 - 40,000	20,000 - 40,000	.0004" - .0005"	.0003" - .0004"
1/16"	20,000 - 40,000	20,000 - 40,000	.0008" - .0010"	.0005" - .0008"
3/32"	20,000 - 40,000	20,000 - 40,000	.0010" - .0015"	.0008" - .0012"
1/8"	20,000 - 40,000	20,000 - 36,000	.0015" - .0020"	.0010" - .0015"
3/16"	20,000 - 32,000	20,000 - 25,000	.0020" - .0030"	.0015" - .0020"
1/4"	18,000 - 25,000	15,000 - 18,000	.0025" - .0040"	.0020" - .0030"
5/16"	14,000 - 19,000	12,000 - 14,000	.0035" - .0050"	.0025" - .0040"
3/8"	12,000 - 16,000	10,000 - 12,000	.0045" - .0060"	.0030" - .0045"
1/2"	9,000 - 12,000	7,500 - 9,000	.0055" - .0080"	.0040" - .0060"
5/8"	6,500 - 9,000	5,000 - 7,000	.0065" - .0090"	.0050" - .0070"
3/4"	5,500 - 7,500	4,000 - 6,000	.0075" - .0100"	.0060" - .0080"
1"	4,000 - 6,000	3,500 - 5,500	.0085" - .0110"	.0070" - .0090"



RADIAL STEP OVER (ae)

AXIAL DEPTH OF CUT (ap)



Roughing	
Axial (ap)	15% - 25% of Dia.
Radial (ae)	20% - 30% of Dia.

Semi-Finishing	
Axial (ap)	5% - 8% of Dia.
Radial (ae)	2% - 5% of Dia.

Finishing	
Axial (ap)	1% - 3% of Dia.
Radial (ae)	.5% - 1% of Dia.

High pressure air is recommended for clearing chips away from the cut.

NOTE - ABOVE ARE STARTING PARAMETERS ONLY. HIGHER RESULTS MAY BE ACHIEVED WITH OPTIMUM CONDITIONS.